



ALTEF is a proprietary fluoropolymer film developed specially for the air sampling market. ALTEF meets or exceeds many of the desired characteristics of Tedlar[®] at a significantly lower cost.

- Low VOC and sulfur background levels.
- Similar stability properties as Tedlar[®] for a wide variety of compounds, including most VOCs.
- Developed as an alternative to Tedlar[®] film for most gas sampling applications.
- Key Features:
 - Suitable for sampling and analysis of most VOCs within 2 days, and many sulfur compounds for up to 24 hours.
 - Abrasion Resistant.
 - Chemically Inert to most acids, aliphatic and aromatic organic compounds, chlorinated solvents, and alcohols.
- Contains no additives, fillers or pigments.
- Choice of nine fitting options.

- Minimal adsorption.
- Superior storage for organics.
- Inherently pure.
- Benefits of ALTEF as compared to Tedlar[®]:
 - Readily available, in stock.
 - Significantly less expensive than Tedlar[®].
 - Lower VOC background than Tedlar[®].
 - Longer storage times for many compounds versus Tedlar[®] bags.
 - Unlike Tedlar[®], ALTEF does not exhibit background levels of DMAC and phenol.

ALTEF is not recommended for ketones or esters in high concentrations (>30%)

ALTEF is not suitable for storing H_2S . Our Multi-Layer Foil bags are the best choice for collecting and storing H_2S .

| Film | Thickness | Tensile Strength | Max. Operating Temp. | Specific Gravity | Oxygen Permeability | Water Vapor Permeability | Carbon Dioxide Permeability |
|---------|-----------|---------------------|-------------------------|---------------------|--------------------------|-----------------------------|--------------------------------|
| ALTEF | .003" | 6100 psi | 150°C (302°F) | 1.78 | 58 cc/m ² x d | 12-15 g/m ² x d | 172 cc/m ² x d |
| Tedlar® | .002" | 8000 psi | 204°C (400°F) | 1.70 | 50 cc/m ² x d | 9-57 g/m ² x d | 172 cc/m ² x d |

Unique Properties of ALTEF compared to Tedlar®